

Product Data Sheet: 230AF

PRODUCT DESCRIPTION: 230AF is a rigid molded sheeter lining in the medium friction range. Recommended for light to medium duty clutch and brake applications; it is available in virtually every drum diameter and shape required.

MECHANICAL PROPERTIES

Specific Gravity (SAE J380)	1.55-1.75
Shore D Hardness (ASTM D2240-68)	68-80
Tensile Strength (ASTM D638)	2000psi min.
Modulus of Rupture (ASTM-D790)	3700psi min.

FRICITION PROPERTIES 230AF

Coefficient of Friction (SAE J661)	
Normal*	.44
Hot*	.39
Wear Rate by Weight (SAE J661)	.016
Friction Code	FF
Maximum Operating Limits	
Rubbing Speed**	5000 fpm
Pressure**	100 psi
Drum Temperature for	500°F
Constant Operation**	

***Note 1.** – Friction values shown are for guide purposes only since values deviate with changes in temperature, pressure and speed. Practical design should include a 25 to 50 percent safety factor.

****Note 2.** – Rubbing speed, drum temperature, and pressure are directly related. Changing any one value will change the others. The values shown represent typical conditions, but are not the ultimate limits of the material.

SAE J661a Test Curves

