

Product Data Sheet: RF 11

PRODUCT DESCRIPTION

RF 11 is a *Non-Asbestos, Non-Metallic, ultra low friction* rigid molded material. The product has exceptional dimensional stability and friction characteristics. RF 11 is non-corrosive, smooth, non-abrasive and keeps the interface temperatures down on brakes. It can be molded into wide range of shapes and sizes to satisfy virtually all industrial applications.

CHARACTERISTICS

Extremely low noise operation

- Excellent fade & recovery
- Excellent wear rate.
- High tensile strength

MECHANICAL PROPERTIES

Specific Gravity (SAE J380) : 1.87 Gogan Hardness (SAE J379A) : 18 Tensile Strength, PSI (ASTM D638) : 3300_{min}

Impact Resistance (ft-lb/inch²) : 2.3

FRICTIONAL PROPERTIES

Coefficient of Friction (SAE J661):

Normal* : 0.15 Hot* : 0.15

Wear Rate (SAE J661)

(inch³/hp-hr) : 0.002_{max} Friction Code : DD


Maximum Operating Limits:


Rubbing Speed** : 7500 fpm Pressure** : 2000 psi


Drum Temperature for

Constant Operation** : 550°F

SAE J661A TEST CURVES







*Note 1. – Friction values shown are for guide purposes only since values deviate with changes in temperature, pressure and speed. Practical design should include a 25 to 50 percent safety factor.

^{**}Note 2. – Rubbing speed, drum temperature, and pressure are directly related. Changing any one value will change the others. The values shown represent typical conditions, but are not the ultimate limits of the material.